

Clear THERMAC

FLOOR SEALER

Product # 055

DESCRIPTION

A modified acrylic resin with excellent clarity, stain resistance and non-yellowing properties, for sealing floors new & old.

USAGE

Recommended for commercial, institutional, educational and industrial use for sealing of decorative stone, concrete, bricks & other masonry surfaces.

DIRECTIONS

Use product as is or thin with xylene for brush or roller application. Thin with toluene for spraying.

One application is sufficient. Normal drying time is 2 hours.

Clean up with xylene or toluene. All surfaces must be completely dry with no chance of rain within 4 hours.

Old surfaces: must be thoroughly cleaned and allowed to dry.

New surfaces: concrete must be at least 45 to 60 days old.

On epoxy, chattahoochee, check for compatibility before coating.

PRODUCT SPECIFICATIONS

APPEARANCE	Clear liquid
REDUCER	Xylene or Toluene
APPLICATION	Brush, roller or Spray
VISCOSITY	25 seconds #4 Ford Cup
SOLIDS	28% by weight
COVERAGE	300 to 550 sq. ft. /gal. Depending of surface.
PACKAGING	55- 35-15 Gallon drums 5 Gallon pails Cases of 6/1 gallon jugs

SAFETY INFORMATION

CAUTION: FLAMMABLE

Keep away from heat, sparks & flame. Keep container away from heat, sparks & flame. Keep container closed when not in use. Do not transfer to an unmarked container. Use with adequate ventilation. Avoid breathing of vapors. Vapor & liquid may be irritating to the skin. Eye protection and gloves should be used. Ground container before transferring.

FIRST AID

INHALATION: Move person to fresh air. Give artificial respiration if not breathing. EYES & SKIN: Wash with large quantities of water. INGESTION: Do not induce vomiting. Seek medical attention.

KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY.

Quality  Chemical

1835 N.E. 144th Street, North Miami, Florida 33181
(305) 944-2837 • (888) 355-5540 • Fax (305) 944-6857
www.QualityChemical.com